

Cold Drawn Steel Fiber - 406 Fiber



Applications:

- Refractory Industry (Temperature up to 1250°C)
- Reinforced & Refractory Castables
- Petrochemical & Oil Industry
- Metallurgy Industry

Chemical Composition (maximum):

C	Si	Mn	P	S	Cr	Al	Others
0.06	0.6	0.6	0.06	0.06	12.0-14.0	3.0-5.0	Balance

Melting Temperature	: 1455-1510 °C
Application Temperature	: 1230 °C
Tensile Strength	: 1180 MPa (N/mm ²)
Density	: 7.10 (g/cm ³)
Microstructure	: Ferritic
Magnetism	: Yes
Length	: Customized 10 - 50 mm
Diameter	: Customized 0.3 - 1.0 mm

HengYang Steel Fiber

Tel: +86-734-8413463

Fax: +86-734-8411922

Mob: +86-17711646910

Email: info@hysteelfiber.com

Web: www.hysteelfiber.com