

Cold Drawn Steel Fiber-CD310



Applications:

- Refractory Industry (Temperature up to 1200°C)
- Reinforced & Refractory Castables
- Petrochemical & Oil Industry
- Metallurgy Industry

Chemical Composition (maximum):

C	Si	Mn	P	S	Cr	Ni	Others
0.08	1.0	2.0	0.045	0.03	24.0-26.0	19.0-22.0	Balance

Melting Temperature	: 1410-1450 °C
Application Temperature	: 1180 °C
Tensile Strength	: 1260 MPa (N/mm ²)
Density	: 7.98 (g/cm ³)
Microstructure	: Austenite
Magnetism	: Non
Length	: Customized 10 - 50 mm
Diameter	: Customized 0.2 - 1.0 mm

HengYang Steel Fiber

Tel: +86-734-8413463

Fax: +86-734-8411922

Mob: +86-17711646910

Email: info@hysteelfiber.com

Web: www.hysteelfiber.com